

MASTERDUR Bio Dipping Hardener (cold) 1000ml Art. Nr. 94301

Cold dipping hardener for the surfaces of the investment models

Usage: Investment model to be heated for 45 min. at 180°C
Dip for 5 seconds in MASTERDUR Liquid
(in glas/plastic bottle with cover) and than dry it by
placing again in the oven; after that cool at room temperature.

Short version for label:

YETIDUR Bio Dipping Hardener Nr. 943-1000
Cold dipping liquid for partial denture

Model to be heated at 180° C in an oven for 45 min.
Dip for 5 seconds
For drying put it again shortly in the oven

Storage in plastic/glas bottle with cover

Dokument:	Erstellt am/von:	geändert am/von:	Revision:	freigegeben am/von:	Seitenzahl:
BA	05.10.2005/TB	05.06.2019/CJ	1	05.06.2019/TB	Seite 1 von 1